


Wire Rope 18xK7+IWS



公称直径 Nominal Diameter (mm)	近似重量 Calculated mass (kg/100 m)		公称抗拉强度 Norminal tesnile Strength (MPa)									
			1570		1670		1770		1870		1960	
			钢丝绳最小破断拉力 Min. Breaking load (kN)									
	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR
14	83.7	921	108	114	115	121	121	128	128	136	134	142
16	109	120	141	149	150	158	159	168	168	177	176	186
18	138	152	178	188	189	200	201	212	212	224	222	235
20	171	188	220	232	234	247	248	262	262	277	274	290
22	207	227	266	281	283	299	300	317	317	335	332	351
24	246	271	317	335	337	356	357	377	377	399	395	418
26	289	318	371	335	395	418	419	443	442	468	464	490
28	335	368	431	393	458	484	486	513	513	542	538	569
30	384	423	495	455	526	556	558	589	589	623	617	653
32	437	481	563	523	599	633	634	671	670	709	702	743
34	494	543	635	595	676	714	716	757	757	800	793	838
36	553	609	712	672	758	801	803	849	848	897	889	940
38	617	679	793	753	844	892	895	946	945	999	991	1050
40	683	752	879	839	935	989	991	1050	1050	1110	1100	1160
42	753	829	969	929	1030	1090	1090	1160	1150	1220	1210	1280
44	827	910	1060	1020	1130	1200	1200	1270	1270	1340	1330	1400
46	904	995	1160	1120	1240	1310	1310	1390	1380	1460	1450	1530
48	984	1080	1270	1230	1350	1420	1430	1510	1510	1590	1580	1670
50	1070	1180	1370	1450	1460	1540	1550	1640	1640	1730	1720	1810
52	1150	1270	1490	1570	1580	1670	1680	1770	1770	1870	1850	1960
54	1250	1370	1600	1690	170 0	1800	1810	1910	1910	2020	2000	2110
56	1340	1470	1720	1820	1830	1940	1940	2050	2050	2170	2150	2270
58	1440	1580	1850	1950	1970	2080	2080	2200	2200	2330	2310	2440
60	1540	1690	1980	2090	2100	2220	2230	2360	2360	2490	2470	2610

Note: All Specifications are approximate. Specifications are subject to change without notice.