

Wire Rope 6x41WS+FC



公称直径 Nominal Diameter (mm)	近似重量 Calculated mass (kg/100 m)		公称抗拉强度 Normal tesnile Strength (MPa)									
			1570		1670		1770		1870		1960	
			钢丝绳最小破断拉力 Min. Breaking load (kN)									
	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR
12	54.7	60.2	74.6	80.5	79.4	85.6	84.1	90.7	88.9	95.9	93.1	100
13	64.2	70.6	87.6	94.5	93.1	100	98.7	106	104	113	109	118
14	84.5	81.9	102	110	108	117	114	124	121	130	127	137
16	97.3	107	133	143	141	152	150	161	158	170	166	179
18	123	135	168	181	179	193	159	204	200	216	210	226
20	152	167	207	224	220	238	234	252	247	266	259	279
22	184	202	251	271	267	288	283	305	299	322	313	338
24	219	241	298	322	317	342	336	363	355	383	373	402
26	257	283	350	378	373	402	395	426	417	450	437	472
28	298	328	406	438	432	466	458	494	484	522	507	547
30	342	376	466	503	496	535	526	567	555	599	582	628
32	389	428	531	572	564	609	598	645	632	682	662	715
34	439	483	599	646	637	687	675	728	713	770	748	807
36	492	542	671	724	714	770	757	817	800	863	838	904
38	549	604	748	807	796	858	843	910	891	961	934	1010
40	608	669	829	894	882	951	935	1010	987	1070	1030	1120
42	670	737	914	986	972	1050	1030	1110	1090	1170	1140	1230
44	736	809	1000	1080	1070	1150	1130	1220	1190	1290	1250	1350
46	804	884	1100	1180	1170	1260	1240	1330	1310	1410	1370	1480
48	876	963	1190	1290	1270	1370	1350	1450	1420	1530	1490	1610
50	950	1040	1300	1400	1380	1490	1460	1580	1540	1660	1620	1740
52	1030	1130	1400	1510	1490	1610	1580	1700	1670	1800	1750	1890
54	1110	1220	1510	1630	1610	1730	1700	1840	1800	1940	1890	2030
56	1190	1310	1620	1750	1730	1860	1830	1980	1940	2090	2030	2190
58	1280	1410	1740	1880	1850	2000	1960	2120	2080	2240	2180	2350
60	1370	1500	1870	2010	1980	2140	2100	2270	2220	2400	2330	2510
62	1460	1610	1990	2150	2120	2290	2250	2420	2370	2560	2490	2680
64	1560	1710	2120	2290	2260	2440	2390	2580	2530	2730	2650	2860

Note: All Specifications are approximate. Specifications are subject to change without notice.