

**Wire Rope 8x37+FC**



公称直径 Nominal Diameter (mm)	近似重量 Calculated mass (kg/100 m)		公称抗拉强度 Norminal tesnile Strength (MPa)									
			1570		1670		1770		1870		1960	
			钢丝绳最小破断拉力 Min. Breaking load (kN)									
	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR
60	1280	1510	1480	1750	1570	1860	1650	1980	1760	2090	1840	2190
62	1370	1610	1580	1870	1680	1990	1780	2110	1880	2230	1970	2340
64	1460	1720	1680	1990	1790	2120	1890	2250	2000	2370	2100	2490
66	1550	1830	1780	2120	1900	2260	2010	2390	2130	2530	2230	2650
68	1650	1940	1890	2250	2020	2390	2140	2540	2260	2680	2370	2810
70	1740	2060	2010	2380	2140	2540	2260	2690	2390	2840	2510	2980
72	1850	2180	2120	2520	2260	2680	2390	2840	2530	3010	2650	3150
74	1950	2300	2240	2670	22390	2830	2530	3000	2670	3170	2800	3330
76	2060	2430	2370	2810	2520	2990	2670	3170	2820	3350	2950	3510
78	2170	2560	2490	2960	2650	3150	2810	3340	2970	3530	3110	3700
80	2280	2690	2620	3110	2790	3310	2960	3510	3120	3710	3270	3890
82	2390	2820	2760	3270	2930	3480	3110	3690	3280	3900	3440	4090
84	2510	2960	2890	3430	3080	3650	3260	3870	3440	4090	3610	4290

Note: All Specifications are approximate. Specifications are subject to change without notice.