

Wire Rope 6x49SWS+IWR



公称直径 Nominal Diameter (mm)	近似重量 Calculated mass (kg/100 m)		公称抗拉强度 Norminal tesnile Strength (MPa)									
			1570		1670		1770		1870		1960	
			钢丝绳最小破断拉力 Min. Breaking load (kN)									
	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR
60	1380	1500	1870	2010	1980	2140	2100	2270	2220	2400	2330	2510
62	1470	1610	1990	2150	2120	2290	2250	2420	2370	2560	2490	2680
64	1570	1710	2120	2290	2260	2440	2390	2580	2530	2730	2650	2860
66	1670	1820	2260	2460	2460	2590	2540	2740	2690	2900	2820	3040
68	1770	1930	2400	2580	2550	2750	2700	2910	2850	3080	2990	3230
70	1880	2050	2540	2740	2700	2910	2860	3090	3020	3260	3170	3420

Note: All Specifications are approximate. Specifications are subject to change without notice.