

Wire Rope 8x41WS+IWR



公称直径 Nominal Diameter (mm)	近似重量 Calculated mass (kg/100 m)		公称抗拉强度 Norminal tesnile Strength (MPa)									
			1570		1670		1770		1870		1960	
			钢丝绳最小破断拉力 Min. Breaking load (kN)									
	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR	纤维芯 SC	钢芯 IWR
16	91.4	111	118	139	125	148	133	157	140	165	147	174
18	116	141	149	176	150	187	168	198	178	210	186	220
20	143	174	184	217	196	231	207	245	219	259	230	271
22	173	211	223	263	237	280	251	295	265	313	278	328
24	206	251	265	313	282	333	299	353	316	373	331	391
26	241	294	311	367	331	391	351	414	370	437	388	458
28	280	341	361	426	384	453	407	480	430	507	450	532
30	321	392	414	489	440	520	467	551	493	582	517	510
32	366	445	471	556	501	592	531	627	561	663	588	694
34	413	503	532	628	566	568	600	708	633	748	664	784
36	463	564	596	704	634	749	672	794	710	839	744	879
38	516	628	664	784	707	834	749	884	701	934	829	979
40	571	696	736	889	783	928	830	980	877	1040	919	1090
42	630	767	811	958	863	1020	915	1080	967	1140	1010	1200
44	691	842	891	1050	947	1120	1000	1190	1050	1250	1110	1310
46	755	920	973	1150	1040	1220	1100	1300	1150	1370	1220	1430
48	823	1000	1060	1250	1130	1330	1190	1410	1260	1480	1320	1560
50	892	1090	1150	1360	1220	1440	1300	1530	1370	1620	1440	1700
52	965	1180	1240	1470	1320	1560	1400	1660	1480	1750	1550	1830
54	1040	1270	1340	1580	1430	1650	1510	1790	1600	1890	1670	1980
56	1120	1360	1440	1700	1530	1810	1630	1920	1720	2030	1800	2130
58	1200	1460	1550	1830	1650	1940	1740	2050	1840	2180	19630	2280
60	1290	1570	1660	1960	1780	2080	1870	2200	1970	2330	2070	2440
62	1370	1670	1770	2090	1880	2220	1990	2350	2110	2490	2210	2610
64	1450	1780	1880	2230	2000	2370	2120	2510	2240	2650	2350	2780

Note: All Specifications are approximate. Specifications are subject to change without notice.